

V•ROD 50

COMPLIES WITH ICC-ES

GLASS FIBER REINFORCED POLYMER (GFRP) REBAR

REVISION: February, 2025

Product Data Sheet - V•ROD 50

		#2 (6 M)	#3 (10 M)	#4 (12 M)	#5 (15 M)	#6 (20 M)	#7 (22 M)	#8 (25 M)	#9 (30 M)	#10 (32 M)
Guaranteed tensile strength* (ASTM D7205)	MPa	1000	1000	1000	1000	1000	1000	900	800	800
	ksi	145	145	145	145	145	145	130.5	116	116
Minimum tensile modulus (ASTM D7205)	GPa	50								
	ksi	7252								
Guaranteed transverse shear capacity (ASTM D7617)	MPa	179								
	ksi	24.7								
Resin		vinylester								
Weight	g/m	77	157	278	431	619	867	1 122	1 420	1 862
	lb/ft	0.052	0.105	0.187	0.290	0.416	0.583	0.754	0.954	1.251
Effective cross-sectional area (including sand coating)** (CSA S806 Annex A)	mm ²	41	81	139	214	309	397	529	670	825
	in ²	0.063	0.126	0.215	0.332	0.479	0.615	0.820	1.039	1.279
Effective diameter	mm	7.2	10.2	13.3	16.5	19.8	22.5	26.0	29.2	32.3
	in	0.284	0.400	0.523	0.650	0.781	0.885	1.022	1.15	1.271
Nominal cross-sectional area (CSA S807 Table 1)	mm ²	32	71	129	199	284	387	510	645	819
	in ²	0.050	0.110	0.199	0.308	0.440	0.599	0.790	1	1.269

COMPLIES WITH THE FOLLOWING STANDARDS:

- CSA S807-19
- GRADE II MTO
- ASTM D7957-22

* The nominal guaranteed tensile strength must not be used to calculate the strength of the bent portion of a bent bar. Instead use the minimum guaranteed tensile strength found in the technical data sheet of bent V•ROD bars.

** Please contact us for dowelling applications.

Development and splice length are available upon request but should be determined by the design engineer.

The guaranteed value presented in this document is the mean value minus 3 times the standard deviation.

It is the responsibility of the design engineers to contact the bar manufacturer to get the latest updates of this technical data sheet (also available at www.fiberglassrebar.com).

For any additional technical results or literature, please contact us.



700, 9^e Rue Nord, Thetford Mines (Quebec) CANADA G6G 6Z5
sales@fiberglassrebar.com
 Phone: 418-335-3202 | Fax: 418-335-5117 | www.fiberglassrebar.com

